



**Technical Characteristics**

Three-layer, three-dimensional drainage geocomposite, consisting of a geonet core, resistant under load, heat-laminated on both sides with geotextiles.  
Geonet core: 100% HDPE (black) – Geotextiles 100% Polypropylene (white) – 1a-quality.

**Geocomposite**

Property	Test Method	Unit	Value <sup>(c)</sup>			
Product Type	---	---	B120		B200	
Product Code	---	---	F0650B1224S		F0650B2024S	
Tensile Strength MD (T <sub>max</sub> ) CMD (T <sub>max</sub> )	DIN EN ISO 10319	kN/m	22 17		32 29	
In-plane Flow Capacity (q <sub>p</sub> ); MD (rigid/rigid) at 20 kPa at 50 kPa at 100 kPa at 200 kPa	DIN EN ISO 12958	l/(m x s)	i = 1	i = 0.1	i = 1	i = 0.1
			1.1	0.25	0.9	0.2
			1.0	0.21	0.8	0.15
			0.9	0.17	0.65	0.11
			0.6	0.12	0.3	0.05
Ply Adhesion	DIN EN ISO 13426-2/B	N/m	150		150	

**Geonet<sup>(a)</sup>**

Property	Test Method	Unit	Value <sup>(c)</sup>
Raw Material	---	---	High Density Polyethylene, black
Density	DIN EN ISO 1183	g/cm <sup>3</sup>	≥ 0.94
Thickness at 20 kPa (d)	DIN EN ISO 9863-1	mm	5

**Geotextiles<sup>(a)</sup>**

Property	Test Method	Unit	Value <sup>(c)</sup>	
Raw Material	---	---	Polypropylene, white	
Unit Weight (ρ <sub>A</sub> )	DIN EN ISO 9864	g/m <sup>2</sup>	120	200
Tensile Strength MD (T <sub>max</sub> ) CMD (T <sub>max</sub> )	DIN EN ISO 10319	kN/m	8 8	14 14
Puncture Resistance (x – s) (F <sub>p</sub> )	DIN EN ISO 12236	N	1,120	1,890
Characteristic Opening Size (O <sub>90</sub> )	DIN EN ISO 12956	μm	100	60
Water Permeability Velocity Index (V <sub>IH50</sub> ) Flux normal to the Plane (q <sub>N</sub> )	DIN EN ISO 11058	mm/s	100	65
		l/(m <sup>2</sup> x s)	100	65

**Durability Characteristics**

Property	Test Method	Unit	Value <sup>(c)</sup>
Carbon Black Content <sup>(b)</sup>	ASTM D 1603	%	2.0 – 3.0
Oxidative Induction Time (OIT) <sup>(b)</sup>	ASTM D 3895 (190°C; Pure O <sub>2</sub> ; 1 atm)	min	100
UV Resistance <sup>(c)</sup>	---	---	to be covered within 2 weeks
Resistance to Oxidation at elevated Oxygen Pressure <sup>(b)</sup> Tensile Strength and Tensile Elongation – retained values after 14 days	EN ISO 13438 (C1; pH 10; 80°C; 5 MPa)	%	no significant change of initial properties

The product information set forth herein contains guiding values, achieved in our laboratories and/or independent testing institutes on basis of valid test standards and reflects our best knowledge at the time of issue. The values are subject to usual variation in production. The constant quality is verified according to ISO 9001:2000.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures. This information is subject to change without prior notice. Please contact GSE for updated information.



**Europe, CIS & Africa Headquarters**  
GSE Lining Technology GmbH  
Normannenweg 28  
20537 Hamburg  
Germany  
Tel.: +49 40 76742-0  
Fax.: +49 40 76742-34  
e-mail: europe@gseworld.de

**Corporate Headquarters**  
GSE Lining Technology, Inc.  
19103 Gundle Road  
Houston, Texas 77073  
USA  
Tel: +1 281 443-8564  
Fax: +1 281 875-6010

**Other Production Facilities & Sales Offices**  
United Kingdom  
Russia  
Turkey  
Australia  
Thailand  
Egypt  
Chile




1213-CPD-4166

09-07-17-FabriNet ST-E B120/200-E



**Product Description**

GSE FabriNet ST-E is a three-layer, three-dimensional drainage geocomposite – providing drainage, filtration and protection function dependent on height of normal load. The drainage core, an x-shaped geonet, is produced from virgin premium grade high density polyethylene (HDPE). The polyethylene resin is designed specifically for durable applications. The geonet is formulated to resist chemical and microbiological attack and thermal ageing and provides outstanding durability. The core is covered on both sides with high quality needlepunched nonwoven polypropylene (PP) geotextiles. The layers are heat-bonded by thermal lamination<sup>(\*)</sup>. GSE FabriNet ST-E provides a high internal shear strength. Due to its very high resistance against creeping GSE FabriNet ST-E can be used under permanent compressive shear strength. GSE FabriNet geocomposites are available in various thicknesses. The tables contain index characteristics. Please contact GSE for information regarding performance of the product under site-specific load, gradient, and boundary conditions.



**Typical Applications**

GSE FabriNet ST-E has been developed to provide drainage function over a broad range of anticipated site loads and gradients, thus providing the possibility to fully/partially replace mineral drainage and filter layers. GSE FabriNet ST-E has been designed for the collection and discharge of rain water (precipitation) and landfill gas in landfill capping systems. Dependent on normal load and sieve size of overlaying mineral layers GSE FabriNet ST-E provides high protection efficiency against puncturing of geomembranes. GSE FabriNet ST-E can also be used in different applications in the civil engineering and the building construction sector. Due to the optimized width and length of GSE FabriNet ST-E installation at site can be realized rapidly and economically.


**Roll Dimensions**

	Unit	Container Load		Truck Load	
		B120	B200	B120	B200
Roll Width (Geonet Core) (approx.) (b) (d)	m	4.1	4.1	4.1	4.1
Roll Length (approx.) (l) (d)	m	70	70	70	65
Roll Area (approx.)	m <sup>2</sup>	287	287	287	266.5

- (\*): All values - unless otherwise noted - are guiding values. Minimum values are within the 95% confidence interval
- (\*\*): Leaving a width of approx. 20 cm without heat-bonding at both edges in the MD / on both sides – enabling sufficient geonet overlapping during installation
- (a): Component properties prior to lamination
- (b): Geonet properties
- (c): Geotextile properties
- (d): Roll width and length have a tolerance of -1%

*The product information set forth herein contains guiding values, achieved in our laboratories and/or independent testing institutes on basis of valid test standards and reflects our best knowledge at the time of issue. The values are subject to usual variation in production. The constant quality is verified according to ISO 9001:2000.*

*This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures. This information is subject to change without prior notice. Please contact GSE for updated information.*



**Europe, CIS & Africa Headquarters**  
**GSE Lining Technology GmbH**  
 Normannenweg 28  
 20537 Hamburg  
 Germany  
 Tel.: +49 40 76742-0  
 Fax.: +49 40 76742-34  
 e-mail: europe@gseworld.de

**Corporate Headquarters**  
**GSE Lining Technology, Inc.**  
 19103 Gundle Road  
 Houston, Texas 77073  
 USA  
 Tel: +1 281 443-8564  
 Fax: +1 281 875-6010

**Other Production Facilities & Sales Offices**  
 United Kingdom  
 Russia  
 Turkey  
 Australia  
 Thailand  
 Egypt  
 Chile



1213-CPD-4166

09-07-17-FabriNet ST-E B120/200-E