



# GSE TunnelLiner - Product Data Sheet

**GSE TunnelLiner** is a highly flexible polyethylene geomembrane specially designed for high-performance tunnel lining applications. **GSE TunnelLiner** consists of a black core layer and two white outer layers, which greatly facilitate visual inspection and is available in two fire resistance grades (B1 and B2). Whether used in a new design or retrofit installation, **GSE TunnelLiner** provides a unique combination of security, sealing integrity and installation efficiency.

Property	Unit	Test Method	Nominal Value			
Thickness (including signal layer) <sup>(0)</sup>	mm	DIN EN ISO 9863-1	2.0	2.5	3.0	3.2
Visual appearance	---		Free of voids, bubbles, cracks			
Lateral skew	mm	DIN 16726-5.2	≤ 50	≤ 50	≤ 50	≤ 50
Waviness	mm		≤ 10	≤ 10	≤ 10	≤ 10
Density (overall)	g/cm <sup>3</sup>	DIN ISO 1183-1/A	0.910 to 0.960 (Dependent on fire resistance rating)			
Tensile properties (each direction)		DIN EN ISO 527-3 Type 5; 100 mm/min				
Stress at break	MPa <sup>(1)</sup>		≥ 22	≥ 22	≥ 22	≥ 22
Elongation at break	%	l <sub>0</sub> = 50 mm	≥ 700	≥ 700	≥ 700	≥ 700
Elastic Modulus <sup>1,2</sup>	N/mm <sup>2</sup>	DIN EN ISO 527-3, PK 5	≤ 100	≤ 100	≤ 100	≤ 100
Tear resistance	N	DIN ISO 34-1/B(a)	140	175	210	224
Puncture resistance	N	DIN EN ISO 12236	2.650	3.400	4.200	4.400
Dimensional stability (each direction)	%	DIN 53377 (100 °C/1h)	± 2	± 2	± 2	± 2
Appearance	---		No bubbles	No bubbles	No bubbles	No bubbles
Melt flow index	g/10 min	DIN EN ISO 1133 (190 °C/5.0 kg)	≤ 3.3	≤ 3.3	≤ 3.3	≤ 3.3
Multiaxial elongation (Specimen diameter = 800 mm)	%	similar to DIN 53861	≥ 50	≥ 50	≥ 50	≥ 50
Seam performance			Failure in parent material (i.e. not in seam)			
Shear test	%	DIN 16726 – 5.7.1	Peel strength ≥ 60 % of 100 % modulus of parent material.			
Peel test	%	DIN 16726 – 5.7.2	No delamination.			
Performance under hydrostatic pressure	---	DIN 16726 – 5.11	Watertight at 0.5 MPa over 72 hours			
Performance in perforation test	mm (height)	DIN 16726 – 5.12	≥ 750 mm	≥ 1000 mm	≥ 1500 mm	≥ 1500 mm
Cold flex performance at -20°C	---	DIN 16726 – 5.14	no cracking			
Long-term thermal stability (80°C, 70 days; each direction)		DIN 16726 – 5.13.3				
Change in tensile strength	%		≤ 20	≤ 20	≤ 20	≤ 20
Change in ultimate elongation	%		≤ 20	≤ 20	≤ 20	≤ 20
Resistance to Aqueous Solutions	%	DIN 16726 – 5.18	Change in tensile strength ≤ 20 (each direction)			
a) in lime milk - Ca(OH) <sub>2</sub>						
b) in sulphuric acid - H <sub>2</sub> SO <sub>3</sub>						
Fire resistance rating	---	DIN 4102	B1 or B2 as ordered			
Roll width <sup>(2,3)</sup>	m	---	7.5	7.5	7.5	7.5
Roll length (approx.) <sup>(2,3)</sup>	m	---	100	80	65	65
Roll weight (approx.)	kg	---	1,420	1,140	1,420	1,510

(0): Special thickness available upon request

(1): 1 MPa = 1 N/mm<sup>2</sup>

(2): Roll widths and lengths have a tolerance of ± 1%.

(3): Special roll lwidth & length available upon request



GSE TunnelLiner is produced at GSE Rechlin plant, Germany

*This information is provided for reference purposes only and is not intended as a warranty or guarantee. GSE assumes no liability in connection with the use of this information. Please check with GSE for current, standard minimum quality assurance procedures. This information is subject to change without prior notice. Please contact GSE for updated information.*

1213-CPD-3881

## Europe, CIS & Africa Headquarters GSE Lining Technology GmbH

Normannenweg 28  
20537 Hamburg  
Germany  
Tel.: +49 40 76742-0  
Fax: +49 40 76742-34  
e-mail: europe@gseworld.de

## Corporate Headquarters GSE Lining Technology, Inc.

Houston, Texas 77073  
USA  
Tel: +1 281 443-8564  
Fax: +1 281 875-6010

## Other Production facilities & Sales Offices

19103 Gundle Road  
Russia  
Turkey  
Australia  
United Kingdom  
Egypt  
Chile



09-07-17-Tunnel-20/32-ISO-E

Visit us at [www.gseworld.com](http://www.gseworld.com)  
A Gundle/SLT Environmental, Inc. Company